

## Micropol E332 Rotational molding powder based on a random EVA copolymer

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

**Material Notes:**

Information provided by Micropol Limited

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Micropol-E332-Rotational-molding-powder-based-on-a-random-EVA-copolymer.php](http://www.lookpolymers.com/polymer_Micropol-E332-Rotational-molding-powder-based-on-a-random-EVA-copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in <sup>3</sup>	ASTM D792
Melt Flow	25 g/10 min	25 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	ASTM D2240
Tensile Strength, Yield	11.7 MPa	1700 psi	ASTM D638
Elongation at Break	800 - 1000 %	800 - 1000 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	65.0 Å°C	149 Å°F	
Ring & Ball Softening Point	110 Å°C	230 Å°F	ASTM E 28

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China