

Micropol Microcene MC123 Metallocene Based Polyethylene Rotational Molding Powder

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Characteristics: reduced fusion, compacting, and crystallization times or lower oven temperatures; improved wall thickness control, improved impact resistance; low warpage; better creep resistance. Information provided by Micropol Limited

Order this product through the following link:

http://www.lookpolymers.com/polymer_Micropol-Microcene-MC123-Metallocene-Based-Polyethylene-Rotational-Molding-Powder.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D792-91
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238-94

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	57	57	ASTM D2240-86
Tensile Strength, Yield	20.0 MPa	2900 psi	50mm/min; ASTM D638M-89
Flexural Modulus	0.750 GPa	109 ksi	2mm/min; ASTM D790-86

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	68.0 Â°C	154 Â°F	ASTM D648-82

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China