

## Micropol Microlin ML91 Linear Polyethylene Rotational Molding Powder

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

### Material Notes:

Information provided by Micropol Limited

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Micropol-Microlin-ML91-Linear-Polyethylene-Rotational-Molding-Powder.php](http://www.lookpolymers.com/polymer_Micropol-Microlin-ML91-Linear-Polyethylene-Rotational-Molding-Powder.php)

Physical Properties	Metric	English	Comments
Density	0.934 g/cc	0.0337 lb/in <sup>3</sup>	ASTM D792
Melt Flow	7.0 - 9.0 g/10 min	7.0 - 9.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	18.0 MPa	2610 psi	50mm/min; ASTM D638-64T
Elongation at Break	300 %	300 %	ASTM D638-64T
Flexural Modulus	0.550 GPa	79.8 ksi	ASTM D760-66
Impact	19 @Temperature -20.0 Â°C	19 @Temperature -4.00 Â°F	J/mm, Falling weight impact; ARM

Thermal Properties	Metric	English	Comments
Vicat Softening Point	108 Â°C	226 Â°F	ASTM D1525
Brittleness Temperature	<= -70.0 Â°C	<= -94.0 Â°F	ASTM D746
Flammability, UL94	V-2	V-2	
Oxygen Index	26 %	26 %	Critical

Descriptive Properties	Value	Comments
British Standard 2782:508A	Zero Burn Rate	
British Standard 476 Part 7	Class 2	
Civil Aviation Authority Spec No 8 Vertical Test	Pass	
Stores Materials Container Fire Test	Pass	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China