

## Mid-Mountain Materials SILTEX® 36 Amorphous Silica Textile

Category : Ceramic , Glass , Glass Fiber , Oxide , Silicon Oxide , Other Engineering Material , Composite Fibers

### Material Notes:

Description: SILTEX is a family of high performance textile fabric that is comprised of high purity, high strength amorphous silica fibers, woven into a strong, flexible fabric designed for use where severe temperature conditions exist. SILTEX 36 is manufactured to a finished weight of 36 ounces per square yard. It's heavier weight and tight 12-harness satin weave makes SILTEX 36 the premium product for maximum protection of personnel and equipment against more severe welding splatter, sparks, grinding of metals, etc. SILTEX 36 is also excellent for use in engineered thermal insulation systems that requiring higher strength and improved thermal properties over the lighter-weight materials. The amorphous silica fibers that make up SILTEX are unaffected by most chemicals, except strong alkalis, hydrofluoric acid or sodium. All SILTEX fabrics are available in standard and pre-shrunk (fired) versions, Fabrics are available with several coating/treatment options that enhance certain properties of the product in order to meet required performance characteristics. Information provided by Mid-Mountain Materials.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mid-Mountain-Materials-SILTEX-36-Amorphous-Silica-Textile.php](http://www.lookpolymers.com/polymer_Mid-Mountain-Materials-SILTEX-36-Amorphous-Silica-Textile.php)

Physical Properties	Metric	English	Comments
Density	0.961 g/cc	0.0347 lb/in <sup>3</sup>	Calculated from weight of 36 oz/sy
Thickness	1270 microns	50.0 mil	nom

Thermal Properties	Metric	English	Comments
Melting Point	1700 °C	3100 °F	
Maximum Service Temperature, Air	982 °C	1800 °F	Continuous
	1260 °C	2300 °F	Intermittent use
Shrinkage	8.00 - 12.0 % @Temperature 982 °C	8.00 - 12.0 % @Temperature 1800 °F	Linear
	<= 3.00 % @Temperature 704 °C, Time 1800 sec	<= 3.00 % @Temperature 1300 °F, Time 0.500 hour	Linear

Descriptive Properties	Value	Comments
Break Strength	Min 270 x 180 lb	nom, warp x fill (1" x 4")
Construction	Woven fabric, 12 harness satin weave	
Material	Amorphous Silica 96-99%	
Packaging		

Descriptive Properties	50 ly per roll or 150 ly master roll Value	Comments
Tolerance	10%	
Width, standard	36 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China