

Mid-Mountain Materials THERMOSEAL® FIBERPAK® M100 Moldable

Category : Ceramic , Other Engineering Material , Ceramic/Metallic Coating

Material Notes:

Description: A family of high temperature moldables designed for a wide variety of uses. THERMOSEAL® FIBERPAK® MOLDABLES may be formed into shapes or linings, pushed into cracks and holes, or spread into thin sections as coating and separating mediums.

APPLICATION: THERMOSEAL® FIBERPAK® MOLDABLES are applied with the fingers, towels, spatulas, or from caulking guns. Gloves should be worn when hand applying. THERMOSEAL® FIBERPAK® MOLDABLES are easily formed to any contour or readily pressed into cracks and smoothed out. Water wet the tool to facilitate smoothing and contouring. Drying consists of removing the liquid portion of the mix usually by use of an external heat source at 220-200°F @ 95-150°C for approximately six hours per inch of thickness. USES: Trough linings for molten metal transfer High temperature sealing and coating Light weight refractory shape manufacture Trough coating and patching Furnace Patching PACKAGING: 11 oz. Caulking tubes 32 oz. Caulking tubes One Gallon Bucket 5 Gallon Buckets 55 Gallon Drums Information provided by Mid-Mountain Materials.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mid-Mountain-Materials-THERMOSEAL-FIBERPAK-M100-Moldable.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0457 lb/in ³	Fired Density at 2000°F
	2.47 g/cc	0.0891 lb/in ³	Wet Density
	1.28 g/cc	0.0463 lb/in ³	Dry Density
	@Temperature 121 °C	@Temperature 250 °F	
Solids Content	65 %	65 %	Wet

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1090 °C	2000 °F	Use Limit
Shrinkage	-9.00 %	-9.00 %	
	@Temperature 1090 °C	@Temperature 2000 °F	

Descriptive Properties	Value	Comments
Alumina	13%	fired
Appearance	Sticky Paste	
Color	Green	
Description	Patch	
Silica	77%	fired

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China