

Misumi Steatite

Category : Ceramic , Oxide , Magnesium Oxide , Silicon Oxide

Material Notes:

MgO-SiO2 Information provided by MISUMI Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Misumi-Steatite.php

Physical Properties	Metric	English	Comments
Density	2.50 g/cc	0.0903 lb/in ³	
Water Absorption	0.000 %	0.000 %	

Mechanical Properties	Metric	English	Comments
Flexural Strength	120 MPa	17400 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	7.40 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	4.11 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 500 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 932 $\text{Å}^\circ\text{F}$	
	8.10 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	4.50 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 800 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 1470 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	2.00 W/m-K	13.9 BTU-in/hr-ft ² - $\text{Å}^\circ\text{F}$	
Melting Point	1557 $\text{Å}^\circ\text{C}$	2835 $\text{Å}^\circ\text{F}$	
Maximum Service Temperature, Air	1000 $\text{Å}^\circ\text{C}$	1830 $\text{Å}^\circ\text{F}$	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+14$ ohm-cm	$\geq 1.00\text{e}+14$ ohm-cm	
Dielectric Constant	5.20	5.20	
Dielectric Strength	≥ 10.0 kV/mm	≥ 254 kV/in	
Dielectric Loss Index	0.000700	0.000700	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China