

Mitsubishi Hostaphan® RN, 30 micron Nominal Thickness Universal Polyethylene Terephthalate Film

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

Material Notes:

Hostaphan® RN is a transparent, biaxially oriented film made of polyethylene terephthalate (PET) and characterized by outstanding physical properties. Hostaphan® RN is the standard product for the following applications: Films for packaging Coating Laminating Metallizing Printing Decorative films Gloss laminations Adhesive tapes Insulation tapes Release Transfer film Release film for thermosetting resins Hot stamping/Roll leaf Information provided by Mitsubishi Polyester Film

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mitsubishi-Hostaphan-RN-30-micron-Nominal-Thickness-Universal-Polyethylene-Terephthalate-Film.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ASTM D1505-68, method C
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	DIN 40634
	@Temperature 150 °C, Time 900 sec	@Temperature 302 °F, Time 0.250 hour	
Linear Mold Shrinkage, Transverse	0.0030 cm/cm	0.0030 in/in	DIN 40634
	@Temperature 150 °C, Time 900 sec	@Temperature 302 °F, Time 0.250 hour	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	260 MPa	37700 psi	Test speed 100%/min.; 50% r.h.; ISO 527-1, ISO 527-3; Sample type 2
Film Tensile Strength at Yield, TD	265 MPa	38400 psi	Test speed 100%/min.; 50% r.h.; ISO 527-1, ISO 527-3; Sample type 2
Film Elongation at Break, MD	>= 130 %	>= 130 %	Test speed 100%/min.; 50% r.h.; ISO 527-1, ISO 527-3; Sample type 2
Film Elongation at Break, TD	100 %	100 %	Test speed 100%/min.; 50% r.h.; ISO 527-1, ISO 527-3; Sample type 2
Modulus of Elasticity	4.40 GPa	638 ksi	MD; Test speed 1%/min.; 50% r.h.; ISO 527-1, ISO 527-3; Sample type 2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Modulus of Elasticity	5.00 GPa	725 ksi	TD; Test speed 1%/min.; 50% r.h.; ISO 527-1, ISO 527-3; Sample type 2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Coefficient of Friction, Static	0.40	0.40	DIN 53375 or ASTM D1894

Optical Properties	Metric	English	Comments
Haze	8.0 %	8.0 %	Enlarged measurement angle; ASTM D1003-61, method A
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Descriptive Properties	Value	Comments
F5-value (MPa)	105	ISO 527-1, ISO 527-3; Sample type 2; TD; Test speed 100%/min.; 23Â°C, 50% r.h.
	110	ISO 527-1, ISO 527-3; Sample type 2; MD; Test speed 100%/min.; 23Â°C, 50% r.h.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China