

Momentive Performance Materials Addisilâ, ¢ 482 E Healthcare Extrusion Grade Heat Cured Rubber

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Silicone, Silicone Rubber

Material Notes:

Heat cured rubber is a high consistency product that can be molded, extruded or calendered using conventional rubber processing equipment to meet a wide range of cost, durability and performance standards. Addisil 482 E is a member of the Addisil Addition Curing Portfolio. It is a platinum (addition/heat) curable, two-part system with a mixing ratio of A:B 1:1. This grade is suitable for extrusion and intended for application in the Healthcare industry.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-Addisil-482-E-Healthcare-Extrusion-Grade-Heat-Cured-Rubber.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity | 1.19 g/cc | 1.19 g/cc | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|-----------|----------|----------|
| Hardness, Shore A | 81 | 81 | |
| Tensile Strength | 9.00 MPa | 1310 psi | |
| Elongation at Break | 400 % | 400 % | |
| Tear Strength | 30.0 kN/m | 171 pli | Die B |

| Optical Properties | Metric | English | Comments |
|-----------------------|--------|---------|--------------------------------|
| Transmission, Visible | 80 % | 80 % | transparent; thickness unknown |

| Compliance Properties | Metric | English | Comments |
|-----------------------|--------|---------|---|
| FDA | Yes | Yes | FDA Indirect food contact - Rubber articles intended for repeated use - FDA Reg 21CFR177.2600 |

| Descriptive Properties | Value | Comments |
|------------------------|--------------------------------------|--|
| Appearance | Transparent | |
| BfR | product is compositionally compliant | Recommendation XV Silicones; post cured (4h/200°C) |
| ISO10993 | yes | 7 ISO 10993 tests applicable to "wet" chemicals |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com



Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China