

## Momentive Performance Materials FPD Boron Nitride (BN) Coating

Category : Ceramic , Nitride , Other Engineering Material , Ceramic/Metallic Coating

### Material Notes:

Can be applied by brush, roller, dipping, or spraying. Can be applied to either hot or cold services although use of water based coatings on surfaces greater than 100°C is not recommended. Multiple coats may be necessary. Dried coatings can be readily handled, smoothed, or polished with a soft, dry cloth. Uses of Advanced Ceramics Corporation boron nitride water based coatings and aerosol spray: Release Agents, Lubricants and Protective Coatings Boron Nitride (BN) remains lubricious and inert even at extremely high temperatures. Coatings made with BN prevent sticking to increase the life of dies/molds, improve product surface finishes, and reduce production times. Metalforming In molten metal and metalforming applications, BN coatings protect surfaces which come in contact with hot and molten metals. BN inhibits corrosion and chemical attack and provides easier release and longer mold/die life. Applications include: casting, stamping, forging and powder metallurgy. Glass Making BN's high temperature lubricating properties make it ideal in glass making where it helps minimize surface defects, improve mold/die life and release, and reduce clean-up time. Most glass formulations will not stick to BN. Plastics/Rubber Producers of injection-molded plastics and elastomers benefit from BN die applications by improved die release and increased production speeds. Sintering Sintering of metallic and ceramic powders is typically done on graphite plates. A coating of BN can essentially eliminate carbon contamination, reactivity and sticking which can occur at sintering temperatures. Welding and Brazing BN coatings are also ideal for welding and furnace brazing. They protect surfaces from weld spatter and provide superior stop-off protection. BN coatings also protect MIG/MAG welding nozzles from weld spatter. Information provided by GE Advanced Ceramics. Information provided by Momentive Performance Materials, formerly GE Advanced Ceramics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Momentive-Performance-Materials-FPD-Boron-Nitride-BN-Coating.php](http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-FPD-Boron-Nitride-BN-Coating.php)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	850 °C	1560 °F	Oxidizing
Maximum Service Temperature, Inert	1800 °C	3270 °F	Inert/Vacuum

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	typical (Boron Nitride Component)

Descriptive Properties	Value	Comments
Application	Release, Forging Lubrication	
Color	White	
Contents Binder	BN/Alumina Bentonite	
Dilution	Per Instructions	
Relative Hardness	2	On a scale of 1-4 with 1 being the hardest.
Solvent Type	Dry	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**