

Momentive Performance Materials HCT-30D Titanium Diboride (TiB2) Powder

Category : Ceramic , Boride

Material Notes:

Grade HCT-30D is tailored for fabrication by the hot-pressing process. Its composition provides for ease and optimizes the mechanical properties of the component shapes. Titanium Diboride Powder Titanium Diboride (TiB2) is produced by GE Advanced Ceramics using a continuous chemical process that controls stoichiometry and particle size to create high purity powder. The shape of the processed crystals are flat, hexagonal platelets. When solidified into shapes, the resultant ceramic is electrically conductive, a property very rare among ceramic materials. This makes it valuable in electrical applications and also enables it to be formed into complex shapes using electrical discharge machining (EDM). TiB2 ceramics also combine superior hardness and corrosion resistance with a high melting point (>2900°C) and good oxidation resistance to 1000°C. Applications: Titanium Diboride powder is a valuable engineering material which can be used in a wide range of specialty applications: (1) electrically conductive composites; (2) complex, sinterable TiB2 shapes; (3) additives for producing specialty ceramic composite materials; (4) refractory material and antioxidant additive that is nonreactive to most molten nonferrous metals and alloys; (5) thermal enhancement additives. Key Properties: Extreme hardness. Nearly as hard as diamond when sintered, TiB2 is tough enough to be used as military armor and is a valuable addition to improve the fracture toughness of ceramic cutting tools and other components. Electrical/Thermal Conductivity An excellent conductor of both electricity and heat makes TiB2 valuable in electronic and specialty applications. Its flat, plate-shaped particles also enhance thermal conductivity when used as a filler in polymeric matrices. Chemical Resistance Titanium Diboride will not react with molten, nonferrous metals including Cu, Zn and Al. This enables TiB2 to be used as crucibles, vacuum metallization components and electrodes when processing these materials. Simplified Fabrication Titanium Diboride may typically be hot-pressed or HIP'd into desired shapes. Additionally, HCT-S powder from Advanced Ceramics can be cold-pressed and sintered into high density, near-net shapes. Electrical conductivity also enables these ceramic forms to be fabricated into close tolerance, complex shapes using EDM techniques. Information provided by Momentive Performance Materials, formerly GE Advanced Ceramics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-HCT-30D-Titanium-Diboride-TiB2-Powder.php

| Physical Properties | Metric | English | Comments |
|-----------------------|------------------------|------------------------|---------------------|
| Particle Size | 14 µm | 14 µm | mean; 99% -325 mesh |
| Specific Surface Area | 0.25 m ² /g | 0.25 m ² /g | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|---------------|-------------------|----------|
| Modulus of Elasticity | 550 GPa | 79800 ksi | |
| Flexural Strength | 350 - 500 MPa | 50800 - 72500 psi | |

| Thermal Properties | Metric | English | Comments |
|--------------------|----------------------|----------------------|----------|
| CTE, linear | 8.10 µm/m-°C | 4.50 µin/in-°F | |
| | @Temperature 20.0 °C | @Temperature 68.0 °F | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------------------|---|-------------------|
| | 55.0 - 125 W/m-K | 382 - 868 BTU-in/hr-ft ² -°F | |
| | @Temperature 2300 °C | @Temperature 4170 °F | |
| Melting Point | 2850 - 2900 °C | 5160 - 5250 °F | |
| Maximum Service Temperature, Air | 1000 °C | 1830 °F | resists oxidation |

| Electrical Properties | Metric | English | Comments |
|------------------------|------------------------------|------------------------------|----------|
| Electrical Resistivity | 0.0000100 - 0.0000300 ohm-cm | 0.0000100 - 0.0000300 ohm-cm | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China