

## Momentive Performance Materials RTV102 White Adhesive Sealant, High Strength Paste

Category: Polymer, Adhesive, Thermoset, Silicone, Silicone, RTV, Adhesive/Sealant Grade

## **Material Notes:**

One-part acetoxy cure. Acetoxy cure silicones are the most commonly used type of RTV materials and are considered GE Silicones' general purpose product line. Typical uses: High strength high performance seal; vertical and overhead use; electrical insulation; protect leads from mechanical shock; protect components from shock and vibration. Data provided by the manufacturer, GE Silicones. GE Silicones became a part of Momentive Performance Materials in 2006.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Momentive-Performance-Materials-RTV102-White-Adhesive-Sealant-High-Strength-Paste.php

| Physical Properties | Metric    | English       | Comments |
|---------------------|-----------|---------------|----------|
| Density             | 1.05 g/cc | 0.0379 lb/in³ |          |

| Mechanical Properties      | Metric   | English | Comments          |
|----------------------------|----------|---------|-------------------|
| Hardness, Shore A          | 30       | 30      |                   |
| Tensile Strength, Ultimate | 2.75 MPa | 399 psi |                   |
| Elongation at Break        | 450 %    | 450 %   |                   |
| Adhesive Bond Strength     | 1.03 MPa | 149 psi | Typical lap shear |

| Thermal Properties               | Metric   | English  | Comments                       |
|----------------------------------|----------|----------|--------------------------------|
| Maximum Service Temperature, Air | 205 °C   | 401 °F   | Continuous useful temperature. |
| Minimum Service Temperature, Air | -60.0 °C | -76.0 °F | Continuous useful temperature. |

| Electrical Properties | Metric           | English          | Comments |
|-----------------------|------------------|------------------|----------|
| Dielectric Constant   | 2.8              | 2.8              |          |
|                       | @Frequency 60 Hz | @Frequency 60 Hz |          |
| Dielectric Strength   | 19.5 kV/mm       | 495 kV/in        |          |

| Processing Properties  | Metric  | English | Comments |
|------------------------|---------|---------|----------|
| Processing Temperature | 25.0 °C | 77.0 °F |          |

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com



Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China