Momentive Performance Materials RTV103 One Component Acetoxy Adhesive Sealant, Black

Category : Polymer , Adhesive , Thermoset , Silicone , Silicone, RTV, Adhesive/Sealant Grade

Material Notes:

RTV series one-component, ready-to-use adhesive sealants are extremely versatile. They cure to a tough, durable, resilient silicone rubber on exposure to atmospheric moisture at room temperature. Acetic acid vapors are released from the sealant surface as a by-product of cure.RTV102, RTV103, RTV108, and RTV109 sealants are standard strength paste consistency products which can be applied to vertical and overhead surfaces where pourable/self-leveling sealants are not practical.Key Performance Properties: One-component productsCapability to cure at room temperature and ambient humiditySelf adhesion propertiesLow temperature flexibilityHigh temperature performanceExcellent weatherability and ozone and chemical resistanceExcellent electrical insulation propertiesApplications: General purpose bonding, sealing, electrical insulation, formed-in-place gaskets. Can be applied to vertical or overhead surfaces.FDA 21 CFR 177.2600 USDA NSF International Std. No. 51GE Silicones became a part of Momentive Performance Materials in 2006.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-RTV103-One-Component-Acetoxy-Adhesive-Sealant-Black.php

| Physical Properties | Metric | English | Comments |
|-----------------------|-------------|-------------|----------|
| Specific Gravity | 1.05 g/cc | 1.05 g/cc | |
| Linear Mold Shrinkage | 0.010 cm/cm | 0.010 in/in | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-----------|----------|--|
| Hardness, Shore A | 30 | 30 | |
| Tensile Strength, Ultimate | 2.75 MPa | 398 psi | |
| Elongation at Break | 450 % | 450 % | |
| Adhesive Bond Strength | 1.37 MPa | 199 psi | At 100% cohesive failure |
| Tear Strength | 7.85 kN/m | 44.8 pli | |
| Peel Strength | 7.01 kN/m | 40.0 pli | At 100% cohesive failure using 1 in. x 8 in. stainless steel screen at 180° pull angle |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|-------------------------|---------------------------|------------|
| | 270 µm/m-°C | 150 µin/in-°F | |
| CTE, linear | @Temperature 20.0 °C | @Temperature 68.0 °F | |
| Thermal Conductivity | 0.209 W/m-K | 1.45 BTU-in/hr-ft²- °F | |
| Maximum Service Temperature, Air | 204 °C | 399 °F | Continuous |

SONGHAN Plastic Technology Co., Ltd.

www.lookpolymers.com email:sales@lookpolymers.com

| Thermal Properties | Metric | English | Comments | |
|-------------------------|----------|----------|----------|--|
| Brittleness Temperature | -60.0 °C | -76.0 °F | | |

| Electrical Properties | Metric | English | Comments |
|-----------------------|------------------|------------------|----------|
| Volume Resistivity | 3.00e+15 ohm-cm | 3.00e+15 ohm-cm | |
| Dielectric Constant | 2.8 | 2.8 | |
| | @Frequency 60 Hz | @Frequency 60 Hz | |
| Dielectric Strength | 20.0 kV/mm | 508 kV/in | |
| Dissipation Factor | 0.0010 | 0.0010 | |
| | @Frequency 60 Hz | @Frequency 60 Hz | |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------|------------|-----------|
| Cure Time | 20.0 min | 0.333 hour | Tack-free |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|----------|
| Application rate | 400 g/min | |
| Color | Black | |
| Consistency | Paste | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China