

## Momentive Performance Materials RTV123 Black Adhesive Sealant, General Purpose Paste

Category : Polymer , Adhesive , Thermoset , Silicone , Silicone, RTV, Adhesive/Sealant Grade

### Material Notes:

One-part modified alkoxy cure. Modified alkoxy materials cure at room temperature and will outgas a small amount of ammonia and some alcohol during cure. Typical uses: General purpose for bonding metals, plastics, and glass. Data provided by the manufacturer, GE Silicones. GE Silicones became a part of Momentive Performance Materials in 2006.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Momentive-Performance-Materials-RTV123-Black-Adhesive-Sealant-General-Purpose-Paste.php](http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-RTV123-Black-Adhesive-Sealant-General-Purpose-Paste.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength, Ultimate	1.72 MPa	249 psi	
Elongation at Break	350 %	350 %	
Adhesive Bond Strength	0.860 MPa	125 psi	Typical lap shear

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	205 Â°C	401 Â°F	Continuous useful temperature.
Minimum Service Temperature, Air	-60.0 Â°C	-76.0 Â°F	Continuous useful temperature.

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.8	2.8	
	@Frequency 60 Hz	@Frequency 60 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	25.0 Â°C	77.0 Â°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**