Momentive Performance Materials RTV5243 Neutral Cure, One Component RTV Adhesive Sealant

Category : Polymer , Adhesive , Thermoset , Silicone , Silicone, RTV, Adhesive/Sealant Grade

Material Notes:

RTV5240 series sealants are alkoxy neutral cure, one-component, ready to use, electronic grade silicone adhesive sealants exhibiting high strength that will maintain a strong bond even when exposed to moist environments. RTV5240 series sealant are true neutral curing silicone sealants that release methyl alcohol during cure while exposed to atmospheric moisture at room temperature. Unlike most alkoxy curing silicone sealants, RTV5240 series cures very rapidly. Key Performance Properties: A non-corrosive curing process that does not produce exothermic heat or corrosive by-products can be used on corrosion-sensitive electrical and electronic equipment with no adverse effectFast green strength build, fast cure (approximately 4x faster than traditional alkoxy sealants)Low odor cure by-productTough and resilient sealant with primerless adhesion to most metals, painted surfaces and plasticsUL recognized component, File number E-36952Superior hydrolytic stability. The RTV5240 series has demonstrated that it is able to maintain adhesion to many substrates after 20 weeks immersion in 60ŰC waterExcellent electrical insulation propertiesWithstands exposure to harsh environments such as chemical, ozone, moisture and weatheringCompatible with sensitive metals and plasticsGood tear resistanceEasy handling with no mixing, heating or solvent hazardsRetains elastomeric properties at temperatures of -75ŰF to 400ŰFApplications: The RTV5240 series are recommended for use in aerospace, automotive, appliance and other industries which incorporate electronic components or sensitive metal or plastic substrates into a finished product. Electronic and integrated circuits, semi conductors, and copper connections are typical applications. These products are also suitable for use in moist environments. The products in this series have fast green strength development and a cure time faster than many two-part sealants. Since they are one-part products, there is no mixing required, and they can be easily dispensed from a simple bulk dispensing pump or cartridges. Base/catalyst ratio control, static mixer maintenance, butterfly testing for mix uniformity, yield loss from base purging, and other activities/costs associated with two-part sealants are eliminated.GE Silicones became a part of Momentive Performance Materials in 2006.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-RTV5243-Neutral-Cure-One-Component-RTV-Adhesive-Sealant.php

| Physical Properties | Metric | English | Comments | |
|----------------------------|-----------|-----------|----------|--|
| Specific Gravity | 1.50 g/cc | 1.50 g/cc | | |
| | | | | |
| Mechanical Properties | Metric | English | Comments | |
| Hardness, Shore A | 40 | 40 | | |
| Tensile Strength, Ultimate | 2.200 MPa | 319.0 psi | | |
| Elongation at Break | 425 % | 425 % | | |

| Electrical Properties | Metric | English | Comments |
|-----------------------|-----------------|-----------------|----------|
| Volume Resistivity | 3.00e+15 ohm-cm | 3.00e+15 ohm-cm | |
| | 2.8 | 2.8 | |

SONGHAN Plastic Technology Co., Ltd.

| Dielectric Constant Electrical Properties | Metric uency 60 Hz | English Willequency 60 Hz | Comments |
|--|--------------------|------------------------------|----------|
| Dielectric Strength | 20.0 kV/mm | 508 kV/in | |
| Dissipation Factor | 0.0010 | 0.0010 | |
| Dissipation ractor | @Frequency 60 Hz | @Frequency 60 Hz | |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------|------------|--------------------|
| Cure Time | 45.0 min | 0.750 hour | Tack-free |
| | 360 min | 6.00 hour | To depth of 3.2 mm |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|----------|
| Application rate | 300 g/min | |
| Color | Black | |
| Sag/Slump | 2.5 mm | |
| Tooling time | 10 min | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China