

Momentive Performance Materials RTV8262 Silicone Rubber Compounds for Potting, Encapsulating and Sealing

Category : Polymer , Adhesive , Thermoset , Silicone , Silicone, RTV, Adhesive/Sealant Grade

Material Notes:

RTV8111, RTV8112 and RTV8262 silicone rubber compounds are two-part silicone elastomers supplied in ready-to-use matched kits containing a base compound and curing agent. Mechanical and electrical properties for specimen cured 72 hours at 25°C and 50% relative humidity. Key Performance Properties: Conforms to the physical and electrical requirements of MIL-S-23586E Non-corrosive to copper Retention of elastomeric properties at high temperature up to 204°C (400°F) continuously for RTV8111 and RTV8112 up to 260°C (500°F) continuously for RTV8262 Excellent adhesion capabilities when used with primer Room temperature cure Composition free of solvents Applications: Typical applications include, but are not limited to the potting of electronic circuit modules, electrical connectors and coils, and other applications in electronics, military/defense and commercial aerospace industries. GE Silicones became a part of Momentive Performance Materials in 2006.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-RTV8262-Silicone-Rubber-Compounds-for-Potting-Encapsulating-and-Sealing.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.47 g/cc	1.47 g/cc	
Viscosity	47000 cP	47000 cP	
Linear Mold Shrinkage	0.00060 cm/cm	0.00060 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	52	52	
Tensile Strength, Ultimate	4.02 MPa	583 psi	
Elongation at Break	150 %	150 %	
Tear Strength	7.55 kN/m	43.1 pli	

Thermal Properties	Metric	English	Comments
CTE, linear	200 µm/m-°C @Temperature 20.0 °C	111 µin/in-°F @Temperature 68.0 °F	
Specific Heat Capacity	1.46 J/g-°C	0.350 BTU/lb-°F	
Thermal Conductivity	0.310 W/m-K	2.15 BTU-in/hr-ft²- °F	
Maximum Service Temperature, Air	204 °C	399 °F	

Minimum Service Temperature, Air Thermal Properties	-54.0 Å°C Metric	-65.2 Å°F English	Comments
---	---------------------	----------------------	----------

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.40e+14 ohm-cm	4.40e+14 ohm-cm	
Dielectric Constant	3.98 @Frequency 1000 Hz	3.98 @Frequency 1000 Hz	
Dielectric Strength	18.5 kV/mm	470 kV/in	
Dissipation Factor	0.017 @Frequency 1000 Hz	0.017 @Frequency 1000 Hz	

Descriptive Properties	Value	Comments
Color	Red	
Consistency	Pourable	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China