

## Momentive Performance Materials Silopren<sup>®</sup>,ç LSR 2540 Liquid Silicone Rubber - Textile Coating

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

### Material Notes:

This LSR elastomer is a specialty grade, two-component, platinum (addition/heat) curable, and pumpable silicone elastomer that can be molded and cured with very fast cycle times, at elevated temperatures. The molding process allows for complex part geometry and exact dimensions. LSR elastomers are generally suitable for short cycle time injection and full automatic flash-less processing. Color pastes are available to pigmenting addition cure productions of LSR's. All LSR grades are platinum cured materials which are mixed in a 1:1 ratio by weight. Industries and Applications: The Momentive portfolio of products is used for a wide variety of applications in the Automotive, Aviation and Aerospace, Consumer Goods, Consumer Electronics, Healthcare and Energy Industries. LSR 2540 is a Textile Coating grade LSR.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Momentive-Performance-Materials-Silopren-LSR-2540-Liquid-Silicone-Rubber-Textile-Coating.php](http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-Silopren-LSR-2540-Liquid-Silicone-Rubber-Textile-Coating.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	
Linear Mold Shrinkage	0.027 cm/cm	0.027 in/in	vulcanized 10 sec at 200°C; Without post-cure
	0.035 cm/cm	0.035 in/in	vulcanized 10 sec at 200°C then post-cured

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength	7.00 MPa	1020 psi	
Elongation at Break	500 %	500 %	
Tear Strength	25.0 kN/m	143 pli	Die B
Compression Set	20 %	20 %	Post cured

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Transmission, Visible	20 %	20 %	translucent; thickness unknown

Compliance Properties	Metric	English	Comments
			FDA Indirect food contact - Rubber

<b>FDA Compliance Properties</b>	<b>Yes Metric</b>	<b>Yes English</b>	<b>Comments</b>
USP Class VI	Yes	Yes	articles intended for repeated use - FDA REG 21CFR177.2600 USP Class VI methods: Intramuscular implantation, intracutaneous injection, & systematic injection

<b>Processing Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Nozzle Temperature	20.0 Â°C	68.0 Â°F	cool nozzle and cylinder to prevent premature vulcanization
Mold Temperature	140 - 230 Â°C	284 - 446 Â°F	short vulcanization time required (a few seconds)
Injection Pressure	5.00 - 15.0 MPa	725 - 2180 psi	depends on feed channel
Hold Pressure	5.00 MPa	725 psi	

<b>Descriptive Properties</b>	<b>Value</b>	<b>Comments</b>
Appearance	Translucent	
BfR	product is compositionally compliant	Recommendation XV Silicones; post cured (4h/200Â°C)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China