

Momentive Performance Materials Silopren[®],ç LSR 2650 ZKS Custom Liquid Silicone Rubber - Automotive

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

This LSR elastomer is a specialty grade, two-component, platinum (addition/heat) curable, and pumpable silicone elastomer that can be molded and cured with very fast cycle times, at elevated temperatures. The molding process allows for complex part geometry and exact dimensions. LSR elastomers are generally suitable for short cycle time injection and full automatic flash-less processing. Color pastes are available to pigmenting addition cure productions of LSR's. All LSR grades are platinum cured materials which are mixed in a 1:1 ratio by weight. Industries and Applications: The Momentive portfolio of products is used for a wide variety of applications in the Automotive, Aviation and Aerospace, Consumer Goods, Consumer Electronics, Healthcare and Energy Industries. LSR 2650 ZKS is a Custom Automotive grade LSR.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-Silopren-LSR-2650-ZKS-Custom-Liquid-Silicone-Rubber-Automotive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	
Linear Mold Shrinkage	0.027 cm/cm	0.027 in/in	vulcanized 10 sec at 200°C; Without post-cure
	0.035 cm/cm	0.035 in/in	vulcanized 10 sec at 200°C then post-cured

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	
Tensile Strength	10.0 MPa	1450 psi	
Elongation at Break	590 %	590 %	
Tear Strength	38.0 kN/m	217 pli	Die B
Compression Set	17 %	17 %	Post cured

Processing Properties	Metric	English	Comments
Nozzle Temperature	20.0 °C	68.0 °F	cool nozzle and cylinder to prevent premature vulcanization
Mold Temperature	140 - 230 °C	284 - 446 °F	short vulcanization time required (a few seconds)
Injection Pressure	5.00 - 15.0 MPa	725 - 2180 psi	depends on feed channel
Hold Pressure	5.00 MPa	725 psi	

Descriptive Properties	Value	Comments
Appearance	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China