

Momentive Performance Materials Silplus,ç 40 MP Heat Cured Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Heat cured rubber is a high consistency product that can be molded, extruded or calendered using conventional rubber processing equipment to meet a wide range of cost, durability and performance standards. Silplus 40 MP is a peroxide curable, multipurpose silicone elastomer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-Silplus-40-MP-Heat-Cured-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength	9.00 MPa	1310 psi	
Elongation at Break	700 %	700 %	
Tear Strength	17.0 kN/m	97.0 pli	Die B

Optical Properties	Metric	English	Comments
Transmission, Visible	20 %	20 %	translucent; thickness unknown

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	FDA Indirect food contact - Rubber articles intended for repeated use - FDA Reg 21CFR177.2600
USP Class VI	Yes	Yes	USP Class VI methods: Intramuscular implantation, intracutaneous injection, & systematic injection

Descriptive Properties	Value	Comments
Appearance	Translucent	
BfR	product is compositionally compliant	Recommendation XV Silicones; post cured (4h/200Å°C)
ISO10993	yes	7 ISO 10993 tests applicable to "wet" chemicals

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China