

Momentive Performance Materials TSE3033 Clear General Purpose Potting/Encapsulating Compound

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone, RTV, Encapsulation Grade

Material Notes:

Two-part addition cure. Two-part addition cure RTV silicones can be cured very quickly with the use of high heat. Addition cure products have no cure by-products and can be used to unlimited depths. Typical uses: Low viscosity, clear uses. Data provided by the manufacturer, GE Silicones. GE Silicones became a part of Momentive Performance Materials in 2006.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-TSE3033-Clear-General-Purpose-PottingEncapsulating-Compound.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Viscosity	1000 cP @Temperature 25.0 °C	1000 cP @Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength, Ultimate	0.980 MPa	142 psi	
Elongation at Break	130 %	130 %	

Thermal Properties	Metric	English	Comments
CTE, linear	230 μm/m-°C @Temperature 20.0 °C	128 μin/in-°F @Temperature 68.0 °F	
Thermal Conductivity	0.170 W/m-K	1.18 BTU-in/hr-ft ² - °F	
Maximum Service Temperature, Air	204 °C	399 °F	Continuous useful temperature.
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	Continuous useful temperature.

Optical Properties	Metric	English	Comments
Refractive Index	1.406	1.406	
Transmission, Visible	90 %	90 %	clear; thickness not quantified

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric 15 ohm-cm	English 5 ohm-cm	Comments
Dielectric Constant	2.8 @Frequency 1000 Hz	2.8 @Frequency 1000 Hz	
Dielectric Strength	21.0 kV/mm @Thickness 1.91 mm	533 kV/in @Thickness 0.0750 in	
Dissipation Factor	0.0010 @Frequency 1000 Hz	0.0010 @Frequency 1000 Hz	

Processing Properties	Metric	English	Comments
Processing Temperature	25.0 Â°C	77.0 Â°F	Cure time 6 hours.
Pot Life	360 min @Temperature 25.0 Â°C	360 min @Temperature 77.0 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China