

## Momentive Performance Materials TUFEL II 94306 Low Volatile Extrusion Heat Cured Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

### Material Notes:

Heat cured rubber is a high consistency product that can be molded, extruded or calendered using conventional rubber processing equipment to meet a wide range of cost, durability and performance standards. TUFEL II Low Volatile 94306 is a member of the Addition Curing Portfolio. It is a platinum (addition/heat) curable, one-part compound. This product has been optimized for extrusion and calendering processes and is intended for application in the Healthcare industry.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Momentive-Performance-Materials-TUFEL-II-94306-Low-Volatile-Extrusion-Heat-Cured-Rubber.php](http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-TUFEL-II-94306-Low-Volatile-Extrusion-Heat-Cured-Rubber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	28	28	
Tensile Strength	9.30 MPa	1350 psi	
Elongation at Break	1050 %	1050 %	
Tear Strength	30.0 kN/m	171 pli	Die B

Optical Properties	Metric	English	Comments
Transmission, Visible	20 %	20 %	translucent; thickness unknown

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	FDA Indirect food contact - Rubber articles intended for repeated use - FDA Reg 21CFR177.2600
USP Class VI	Yes	Yes	USP Class VI methods: Intramuscular implantation, intracutaneous injection, & systematic injection

Descriptive Properties	Value	Comments
Appearance	Translucent	
BfR	product is compositionally compliant	Recommendation XV Silicones; post cured (4h/200°C)

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China