

Momentive Performance Materials TUFEL™ II 94606 Low Volatile Extrusion Heat Cured Rubber

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Silicone, Silicone Rubber

Material Notes:

Heat cured rubber is a high consistency product that can be molded, extruded or calendered using conventional rubber processing equipment to meet a wide range of cost, durability and performance standards. TUFEL II Low Volatile 94606 is a member of the Addition Curing Portfolio. It is a platinum (addition/heat) curable, one-part compound. This product has been optimized for extrusion and calendering processes and is intended for application in the Healthcare industry.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-TUFEL-II-94606-Low-Volatile-Extrusion-Heat-Cured-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	62	62	
Tensile Strength	8.60 MPa	1250 psi	
Elongation at Break	690 %	690 %	
Tear Strength	46.0 kN/m	262 pli	Die B

Optical Properties	Metric	English	Comments
Transmission, Visible	20 %	20 %	translucent; thickness unknown

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	FDA Indirect food contact - Rubber articles intended for repeated use - FDA Reg 21CFR177.2600
USP Class VI	Yes	Yes	USP Class VI methods: Intramuscular implantation, intracutaneous injection, & systematic injection

Descriptive Properties	Value	Comments
Appearance	Translucent	
BfR	product is compositionally compliant	Recommendation XV Silicones; post cured (4h/200°C)

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China