

Momentive Performance Materials XE23-703U Heat Cured Rubber - Electro Conductive

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Silicone, Silicone Rubber

Material Notes:

Heat cured rubber is a high consistency product that can be molded, extruded or calendered using conventional rubber processing equipment to meet a wide range of cost, durability and performance standards.XE23-703U is a specialty grade, peroxide curable silicone elastomer.Key Feature: Vol. Res. 3 Ohm/cm

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-XE23-703U-Heat-Cured-Rubber-Electro-Conductive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	
Tensile Strength	6.00 MPa	870 psi	
Elongation at Break	240 %	240 %	
Tear Strength	16.0 kN/m	91.3 pli	angle

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.0 ohm-cm	3.0 ohm-cm	

Descriptive Properties	Value	Comments
Appearance	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China