

Monmouth Rubber & Plastics Durafoam, C42 Closed Cell Epichlorohydrin

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Information provided by Monmouth Rubber & Plastics Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Monmouth-Rubber-Plastics-Durafoam-C42-Closed-Cell-Epichlorohydrin.php

Physical Properties	Metric	English	Comments
Density	0.240 g/cc	0.00868 lb/in ³	ASTM D1056
Water Absorption	<= 5.0 %	<= 5.0 %	Weight change; ASTM D1056

Mechanical Properties	Metric	English	Comments
Tensile Strength	0.621 MPa	90.0 psi	Die A; ASTM D412
Elongation at Break	175 %	175 %	Die A; ASTM D412
Compressive Strength	0.0345 - 0.0621 MPa	5.00 - 9.00 psi	Deflection @ 25%; ASTM D1056
Tear Strength	3.51 kN/m	20.0 pli	Die C; ASTM D624
Compression Set	<= 25 %	<= 25 %	ASTM D1056

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	-40.0 Â°C	-40.0 Â°F	
Minimum Service Temperature, Air	149 Â°C	300 Â°F	
	325 Â°C	617 Â°F	Intermittent

Descriptive Properties	Value	Comments
Color	Black	
Fluid Immersion	<50%	(7 days at 73.4Â°F) ASTM Ref. Fuel B, Weight Change, ASTM-D-1056
Resilience	0.3	ASTM D2632

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China