

Monmouth Rubber & Plastics Durafoam™,ç DK2121 NEO/EPDM Polymeric Blend

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Information provided by Monmouth Rubber & Plastics Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Monmouth-Rubber-Plastics-Durafoam-DK2121-NEOEPDM-Polymeric-Blend.php

Physical Properties	Metric	English	Comments
Density	0.0641 - 0.128 g/cc	0.00231 - 0.00463 lb/in ³	
Water Absorption	<= 5.0 %	<= 5.0 %	10% allowed

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 0.689 MPa	>= 100 psi	
Elongation at Break	>= 150 %	>= 150 %	
Compressive Strength	0.0345 - 0.0621 MPa	5.00 - 9.00 psi	Deflection @ 25%

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	-40.0 Â°C	-40.0 Â°F	
Minimum Service Temperature, Air	121 Â°C	250 Â°F	

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China