

## Monmouth Rubber & Plastics Durafoam™,ç DK3131 NEO/EPDM Polymeric Blend

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

Information provided by Monmouth Rubber & Plastics Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Monmouth-Rubber-Plastics-Durafoam-DK3131-NEOEPDM-Polymeric-Blend.php](http://www.lookpolymers.com/polymer_Monmouth-Rubber-Plastics-Durafoam-DK3131-NEOEPDM-Polymeric-Blend.php)

Physical Properties	Metric	English	Comments
Density	0.112 - 0.176 g/cc	0.00405 - 0.00637 lb/in <sup>3</sup>	
Water Absorption	<= 5.0 %	<= 5.0 %	10% allowed

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 0.689 MPa	>= 100 psi	
Elongation at Break	>= 150 %	>= 150 %	
Compressive Strength	0.0621 - 0.0896 MPa	9.00 - 13.0 psi	Deflection @ 25%

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	-40.0 Â°C	-40.0 Â°F	
Minimum Service Temperature, Air	121 Â°C	250 Â°F	

Descriptive Properties	Value	Comments
Color	Black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China