

Multibase C6-265 DI-CUP R Dow-Corning Class VI Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-C6-265-DI-CUP-R-Dow-Corning-Class-VI-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	64	64	molded- without post cure; ASTM D2240
	70	70	post cured- 4 hours at 177Â°C; ASTM D2240
	71	71	post cured- 2 hours at 177Â°C; ASTM D2240
	73	73	post cured- 8 hours at 177Â°C; ASTM D2240
Tensile Strength, Ultimate	7.58 MPa	1100 psi	molded-without post cure; ASTM D412
	7.58 MPa	1100 psi	post cured- 2 hours at 177Â°C; ASTM D412
	7.58 MPa	1100 psi	post cured- 4 hours at 177Â°C; ASTM D412
	8.27 MPa	1200 psi	post cured- 8 hours at 177Â°C; ASTM D412
Tensile Strength, Yield	3.03 MPa	440 psi	at 200%, molded-without post cure; ASTM D412
	4.14 MPa	600 psi	200%, post cured- 4 hours at 177Â°C; ASTM D412
	4.21 MPa	610 psi	at 200%, post cured- 2 hours at 177Â°C; ASTM D412
	4.55 MPa	660 psi	200%, post cured- 8 hours at 177Â°C; ASTM D412
Elongation at Break	430 %	430 %	post cured- 8 hours at 177Â°C; ASTM D412
	430 %	430 %	post cured- 2 hours at 177Â°C; ASTM D412
	450 %	450 %	post cured- 4 hours at 177Â°C; ASTM D412
	620 %	620 %	molded-without post cure; ASTM D412
Tear Strength	33.3 kN/m	190 pli	Die B, post cured- 4 hours at 177Â°C; ASTM D624

Mechanical Properties	Metric	English	Comments
	33.1 kN/m	190 pli	Die B, post cured- 8 hours at 177Å°C; ASTM D624
	35.1 kN/m	200 pli	Die B, post cured- 2 hours at 177Å°C; ASTM D624
	40.3 kN/m	230 pli	Die B, molded-without post cure; ASTM D624
Compression Set	52 %	52 %	22 hours at 177Å°C, post cured- 2 hours at 177Å°C; ASTM D395
	74 %	74 %	22 hours at 177Å°C, molded-without post cure; ASTM D395
	83 %	83 %	22 hours at 177Å°C, post cured- 4 hours at 177Å°C; ASTM D395
	91 %	91 %	22 hours at 177Å°C, post cured- 8 hours at 177Å°C; ASTM D395

Thermal Properties	Metric	English	Comments
Shrinkage	2.70 %	2.70 %	post cured
	@Temperature 177 Å°C, Time 14400 sec	@Temperature 351 Å°F, Time 4.00 hour	
	3.20 %	3.20 %	
	@Temperature 177 Å°C, Time 7200 sec	@Temperature 351 Å°F, Time 2.00 hour	post cured
	3.20 %	3.20 %	post cured
	@Temperature 177 Å°C, Time 28800 sec	@Temperature 351 Å°F, Time 8.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China