

## Multibase Multi-ABS 7522 R , 22% Filler Content

Category : Polymer , Thermoplastic , ABS Polymer

**Material Notes:**

Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-ABS-7522-R-22-Filler-Content.php](http://www.lookpolymers.com/polymer_Multibase-Multi-ABS-7522-R-22-Filler-Content.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	ASTM D792-91
Melt Flow	2.8 g/10 min	2.8 g/10 min	(Condition I) ASTM D-1238-94a

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	51.7 MPa	7500 psi	ASTM D638-95
Elongation at Break	12 %	12 %	ASTM D638-95
Flexural Strength	75.9 MPa	11000 psi	ASTM D790-95
Flexural Modulus	5.172 GPa	750.1 ksi	Method 1, Proc. B; ASTM D-790-95
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256-93a

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	
	@Thickness 1.59 mm	@Thickness 0.0625 in	
	HB	HB	
	@Thickness 3.17 mm	@Thickness 0.125 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China