

Multibase Multi-ABS 8933 Black

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Ash is 28% per ASTM D-5630-94.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-ABS-8933-Black.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ASTM D792-91
Linear Mold Shrinkage	0.0024 cm/cm	0.0024 in/in	ASTM D955-89
Melt Flow	3.9 g/10 min	3.9 g/10 min	(Condition I) ASTM D-1238-94a

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	43.3 MPa	6280 psi	ASTM D638-95
Elongation at Break	16.3 %	16.3 %	ASTM D638-95
Flexural Strength	65.5 MPa	9500 psi	ASTM D790-95
Flexural Modulus	5.903 GPa	856.2 ksi	RT; ASTM D-790-95
Izod Impact, Notched	0.610 J/cm	1.14 ft-lb/in	ASTM D256-93a

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China