

Multibase Multi-Flex[®] A 4001 LC Black TPE Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Features: Heat Resistance, HighOzone ResistantCompression Set, Low Forms: PelletsProcessing Method:Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-A-4001-LC-Black-TPE-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM 792
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	ASTM D955
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 230 Å°C	2.0 g/10 min @Load 4.76 lb, Temperature 446 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	33	33	10 seconds; ASTM D2240
Tensile Strength, Yield	5.50 MPa	798 psi	Elastic; ASTM D412
	0.827 MPa @Strain 100 %	120 psi @Strain 100 %	ASTM D412
Elongation at Break	600 %	600 %	Elastic; ASTM D412
Tear Strength	17.5 kN/m	100 pli	ASTM D624
Compression Set	11 %	11 %	73Å°F, 70 hours; ASTM D395
	39 %	39 %	158Å°F, 70 hours; ASTM D395

Thermal Properties	Metric	English	Comments
Flame Spread	38 mm/min	1.5 in/min	VSS-302

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	210 Å°C	410 Å°F	
Front Barrel Temperature	227 Å°C	440 Å°F	
Nozzle Temperature	235 Å°C	455 Å°F	
Mold Temperature	51.7 Å°C	125 Å°F	

Processing Properties

Metric: 0 %

English: 0 %

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China