

Multibase Multi-Flex® A 6221 CUV A Black TPE Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-A-6221-CUV-A-Black-TPE-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM 792
Melt Flow	70 g/10 min @Load 2.16 kg, Temperature 230 °C	70 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	64	64	10 seconds; ASTM D2240
Tensile Strength, Yield	3.45 MPa	500 psi	Elastic; ASTM D412
	1.86 MPa @Strain 100 %	270 psi @Strain 100 %	ASTM D412
Elongation at Break	500 %	500 %	ASTM D412
Tear Strength	22.8 kN/m	130 pli	ASTM D624

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	210 °C	410 °F	
Front Barrel Temperature	227 °C	440 °F	
Nozzle Temperature	235 °C	455 °F	
Mold Temperature	51.7 °C	125 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China