

## Multibase Multi-Flex<sup>®</sup> A 8502 A Black TPE Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer , TPE

**Material Notes:**

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-A-8502-A-Black-TPE-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-A-8502-A-Black-TPE-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM 792
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	10 seconds; ASTM D2240
Tensile Strength, Yield	7.58 MPa	1100 psi	Elastic; ASTM D412
Elongation at Break	600 %	600 %	Elastic; ASTM D412
Flexural Modulus	0.112 GPa	16.3 ksi	ASTM D790
Tear Strength	42.1 kN/m	240 pli	ASTM D624

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China