

Multibase Multi-Flex® TPE A 6821 C BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The burn rate is 1 in/min (25 mm/min) based on ASTM FM VSS 302. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-6821-C-BLK.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	ASTM D955
Melt Flow	8.0 - 15 g/10 min	8.0 - 15 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	10 sec; ASTM D-2240
Tensile Strength, Ultimate	5.50 MPa	798 psi	ASTM D412
Elongation at Break	>= 500 %	>= 500 %	ASTM D412
Flexural Modulus	0.0410 GPa	5.95 ksi	method 1, Proc.B; ASTM D-790
Tear Strength	24.5 kN/m	140 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China