

Multibase Multi-Flex® TPE A 7318 GREY

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The burn rate is 1 in/min (25 mm/min) based on ASTM FM VSS 302. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-7318-GREY.php

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	ASTM D955
Melt Flow	10 - 15 g/10 min	10 - 15 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	10 sec; ASTM D-2240
Tensile Strength, Ultimate	8.30 MPa	1200 psi	ASTM D412
Elongation at Break	>= 600 %	>= 600 %	ASTM D412
Flexural Modulus	0.0345 GPa	5.00 ksi	method 1, Proc.B; ASTM D-790
Tear Strength	>= 8.30 kN/m	>= 47.4 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China