

Multibase Multi-Flex® TPE A 7606 BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The burn rate is 1.2 in/min (30 mm/min) based on ASTM FM VSS 302. Multi-Flex TPE contains Kraton™ G. Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-7606-BLK.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D792
Melt Flow	2.2 g/10 min	2.2 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	10 sec; ASTM D-2240
Tensile Strength, Ultimate	>= 7.45 MPa	>= 1080 psi	ASTM D412
Elongation at Break	>= 400 %	>= 400 %	ASTM D412
Tear Strength	>= 24.5 kN/m	>= 140 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China