

Multibase Multi-Flex® TPE A 7606 GREY

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The burn rate is 1 in/min (25 mm/min) based on ASTM FM VSS 302. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-7606-GREY.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.016 cm/cm	0.016 in/in	ASTM D955
Melt Flow	1.3 g/10 min	1.3 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	10 sec; ASTM D-2240
Tensile Strength, Ultimate	>= 1.17 MPa	>= 170 psi	ASTM D412
Elongation at Break	>= 400 %	>= 400 %	ASTM D412
Tear Strength	>= 39.4 kN/m	>= 225 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China