

Multibase Multi-Flex® TPE A 8502 P BLK , 37.5% Filler Content

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The following data represents the actual data obtained from Lot # 941101-5. The moisture content is 0.03%. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-8502-P-BLK-375-Filler-Content.php

Physical Properties	Metric	English	Comments
Density	0.998 g/cc	0.0361 lb/in ³	ASTM D792
Melt Flow	15 g/10 min	15 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	92	92	10 sec; ASTM D-2240
Tensile Strength, Ultimate	9.70 MPa	1410 psi	ASTM D638
Elongation at Break	635 %	635 %	ASTM D638
Tear Strength	50.7 kN/m	289 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China