

## Multibase Multi-Flex® TPE A 9002-SR BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

**Material Notes:**

Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-TPE-A-9002-SR-BLK.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-9002-SR-BLK.php)

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	7.0 g/10 min	7.0 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	89	89	10 sec; ASTM D-2240
Tensile Strength, Ultimate	8.90 MPa	1290 psi	ASTM D412
Elongation at Break	527 %	527 %	ASTM D412
Flexural Modulus	0.117 GPa	17.0 ksi	method 1, Proc.B; ASTM D-790
Tear Strength	3.40 kN/m	19.4 pli	ASTM D624

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China