

Multibase Multi-Flex® TPE A 9502 BLK , 7% Filler Content

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The moisture content is 0.02%. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-9502-BLK-7-Filler-Content.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792
Melt Flow	15.51 g/10 min	15.51 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91.4	91.4	10 sec; ASTM D-2240
Tensile Strength, Ultimate	14.5 MPa	2100 psi	ASTM D412
Elongation at Break	675 %	675 %	ASTM D412
Flexural Strength	6.30 MPa	914 psi	
Flexural Modulus	0.193 GPa	28.0 ksi	method 1, Proc.B; ASTM D-790
Tear Strength	71.5 kN/m	408 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China