

## Multibase Multi-Flex® TPE RP 6568 C BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

### Material Notes:

This product was developed for soft touch airbag covers and contains Kraton G form Shell. The fogging test value is 70% according to ASTM GM 9305P. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-TPE-RP-6568-C-BLK.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-RP-6568-C-BLK.php)

Physical Properties	Metric	English	Comments
Density	0.890 g/cc	0.0322 lb/in <sup>3</sup>	ASTM D792
Melt Flow	10 - 20 g/10 min	10 - 20 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	44	44	10 sec; ASTM D-2240
Tensile Strength, Ultimate	2.80 MPa	406 psi	ASTM D412
Elongation at Break	800 %	800 %	ASTM D412
Tear Strength Test	17.5 - 24.5	17.5 - 24.5	ASTM D624

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China