

Multibase Multi-Flex® TPE RP 6568 C340 BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

This product was designed for 2 shot airbag covers with lower tensile strength than currently in use. Ash is 2.2%. The moisture content is 0.05%. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-RP-6568-C340-BLK.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ASTM D792
Melt Flow	18 g/10 min	18 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	56	56	10 sec; ASTM D-2240
Tensile Strength, Ultimate	2.90 MPa	421 psi	20"/min.; ASTM D-412
Elongation at Break	820 %	820 %	ASTM D638
Tear Strength	24.5 kN/m	140 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China