

Multibase Multi-Pro® 2502 CU Black Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-2502-CU-Black-Polypropylene.php

Physical Properties	Metric	English	Comments
Ash	24.46 %	24.46 %	ISO 3451/1

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	0.147 J/cm	0.275 ft-lb/in	73°F; ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	72.2 °C	162 °F	Unannealed; ASTM D648
Flame Spread	7.9 mm/min	0.31 in/min	ISO 3795

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China