

## Multibase Multi-Pro® 2518 TU Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

Talc Filled, 25% by weight. Forms: Pellets Processing Methods: Injection Molding Uses: Automotive Under the Hood Information provided by Multibase

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Pro-2518-TU-Polypropylene.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-2518-TU-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	ASTM D955
Melt Flow	18 g/10 min	18 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.6 MPa	4300 psi	ASTM D638
Elongation at Break	45 %	45 %	ASTM D638
Flexural Modulus	2.21 GPa	320 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	73°F; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	116 °C	240 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	199 - 221 °C	390 - 430 °F	
Middle Barrel Temperature	204 - 232 °C	400 - 450 °F	
Front Barrel Temperature	204 - 232 °C	400 - 450 °F	
Nozzle Temperature	193 - 227 °C	380 - 440 °F	
Mold Temperature	4.44 - 65.6 °C	40.0 - 150 °F	
Drying Temperature	93.3 °C	200 °F	
Dry Time	2 hour	2 hour	
Back Pressure	0.138 - 0.345 MPa	20.0 - 50.0 psi	
Screw Speed			

Processing Properties	40 - 100 rpm Metric	40 - 100 rpm English	Comments
Descriptive Properties		Value	Comments
Clamp Tonnage		2-4 tons/in <sup>2</sup>	
Screw L/D Ratio		20:1	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China