

Multibase Multi-Pro® 3011 CHI Grey 29% Filler Content Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-3011-CHI-Grey-29-Filler-Content-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	ASTM D792-91
Melt Flow	11 g/10 min	11 g/10 min	(Condition L) ASTM D-1238-94a

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	15.2 MPa	2200 psi	ASTM D638-95
Elongation at Break	>= 500 %	>= 500 %	ASTM D638-95
Flexural Strength	20.0 MPa	2900 psi	ASTM D790-95
Flexural Modulus	0.931 GPa	135 ksi	Method 1, Proc. B; ASTM D-790-95
Izod Impact, Notched	NB	NB	ASTM D-256-93a
Gardner Impact	10.2 J	7.52 ft-lb	ASTM D5420-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China