

## Multibase Multi-Pro® 4013 CU Yellow 40% Filler Content Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

**Material Notes:**

Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Pro-4013-CU-Yellow-40-Filler-Content-Polypropylene.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-4013-CU-Yellow-40-Filler-Content-Polypropylene.php)

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	ASTM D955-89
Melt Flow	13 g/10 min	13 g/10 min	(Condition L) ASTM D-1238-94a

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	20.7 MPa	3000 psi	ASTM D638-95
Elongation at Break	200 %	200 %	ASTM D638-95
Flexural Strength	35.9 MPa	5210 psi	ASTM D790-95
Flexural Modulus	2.241 GPa	325.0 ksi	Method 1, Proc. B; ASTM D-790-95
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256-93a
Gardner Impact	11.3 J	8.33 ft-lb	ASTM D5420-93

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China