

## Multibase Multi-Pro® 4810 C White 47.7% Filler Content Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

**Material Notes:**

Moisture content is 0.04%. Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Pro-4810-C-White-477-Filler-Content-Polypropylene.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-4810-C-White-477-Filler-Content-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in <sup>3</sup>	ASTM D792
Melt Flow	15.2 g/10 min	15.2 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	12.8 MPa	1860 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Flexural Strength	22.5 MPa	3260 psi	ASTM D790-92
Flexural Modulus	1.579 GPa	229.0 ksi	Method 1, Proc. B; ASTM D-790
Izod Impact, Notched	2.56 J/cm	4.80 ft-lb/in	ASTM D256-93a
Gardner Impact	15.4 J	11.4 ft-lb	ASTM D5420-93

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China