

Multibase Multi-Pro® 7518 C Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Pro-7518-C-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.72 g/cc	0.0621 lb/in ³	ASTM D792
Water Absorption	0.080 %	0.080 %	at Equilibrium; ASTM D570
Melt Flow	17 g/10 min @Load 2.16 kg, Temperature 230 °C	17 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China