

NCMT NanoPAC™ G2030I High Performance Polypropylene Nanocomposite

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Applications: Construction Material Information provided by Nano Composite Materials Technology Limited

Order this product through the following link:

http://www.lookpolymers.com/polymer_NCMT-NanoPAC-G2030I-High-Performance-Polypropylene-Nanocomposite.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	NCMT Method
Melt Flow	6.0 g/10 min @Load 2.16 kg, Temperature 230 °C	6.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	30.0 MPa	4350 psi	ASTM D638
Elongation at Break	9.0 %	9.0 %	ASTM D638
Tensile Modulus	3.20 GPa	464 ksi	ASTM D638
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	160 °C	320 °F	Deflection Temp.; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China