

NCMT NanoPAC™ HG537 High Performance Polypropylene Nanocomposite

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Applications: Household Industry Electrical Appliances Information provided by Nano Composite Materials Technology Limited

Order this product through the following link:

http://www.lookpolymers.com/polymer_NCMT-NanoPAC-HG537-High-Performance-Polypropylene-Nanocomposite.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	NCMT Method
Melt Flow	13 g/10 min @Load 2.16 kg, Temperature 230 °C	13 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	<= 600 %	<= 600 %	ASTM D638
Tensile Modulus	1.90 GPa	276 ksi	ASTM D638
Izod Impact, Notched	1.68 J/cm	3.15 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	110 °C	230 °F	Deflection Temp.; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China