

ND Industries 567 Shaft & Bearing Retainer Retaining Compound

Category : Polymer , Adhesive , Thermoset

Material Notes:

High temperature retainer for engine cylinder liners and heat exchanger tubes

Order this product through the following link:

http://www.lookpolymers.com/polymer_ND-Industries-567-Shaft-Bearing-Retainer-Retaining-Compound.php

Physical Properties	Metric	English	Comments
Viscosity	6300 - 7700 cP	6300 - 7700 cP	

Mechanical Properties	Metric	English	Comments
Shear Strength	13.8 - 20.7 MPa	2000 - 3000 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	With Primer (Fixture)
	30.0 min	0.500 hour	On steel (Fixture)
	1440 min	24.0 hour	On Steel (Full)
	1440 min	24.0 hour	With Primer (Full)

Descriptive Properties	Value	Comments
Color	Green	
Gap Fill, in.	0.015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China