

## ND Industries 732 Gasket Maker Flexible

Category : Polymer , Thermoset

**Material Notes:**

Flexible Parts. General Purpose

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ND-Industries-732-Gasket-Maker-Flexible.php](http://www.lookpolymers.com/polymer_ND-Industries-732-Gasket-Maker-Flexible.php)

Physical Properties	Metric	English	Comments
Viscosity	275000 - 950000 cP	275000 - 950000 cP	Thixotropic

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	>= 149 °C	>= 300 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	With primer (Fixture)
	60.0 min	1.00 hour	On steel (Fixture)
	120 min	2.00 hour	With primer (Full)
	720 min	12.0 hour	On steel (Full)

Descriptive Properties	Value	Comments
Color	Purple	
Cured Form	Flexible	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China